JEASPAN C-PURLINS



Tibay Laban sa KALAWANG Basta't Galbanisado



DURABLE

Corrosion-resistant
Can stand years of exposure

ECONOMICAL

Less labor cost

Less maintenance needs

Comes in different sizes of 3, 4, 6 & 7 inches
Available thickness of 0.7mm up to 1.6mm in standard 6m and cut-to-size length





ON SOLUTIONS, INC

533 Commonwealth Avenue Matandang Balara 1119 Quezon City Tel. Nos.: (02) 8847-8335



www.jeamaxx.com customerservice@jeamaxx.com



Gross Section Properties C-Sections with Lips

75, 100, 150, 175


	Dimension							Properties of Full Section												
ID	D	В	t	d	R	Area	wt/m	Axis-x-x			Axis-y-y									
								l _x	Sx	r _x	lу	Sy	Гy	Χ	m	J	Cw	j	ro	Хо
	mm	mm	mm	mm	mm	mm ²	kg	1x10 ³ mm ⁴	1x10 ³ mm ³	mm	1x10 ³ mm	1x10 ³ mm ³	mm	mm	mm	mm⁴	1x10 mm	mm	mm	mm
JEA175CS50x1.45	175	50	1.45	20.0	5.00	448.01	3.508	1,808.960	20.674	63.54	149.951	4.174	18.29	14.07	21.72	313.98	1024.929	90.87	74.85	-35.07
JEA175CS50x1.15	175	50	1.15	20.0	5.00	356.40	2.791	1,445.484	16.520	63.68	120.896	3.362	18.42	14.04	21.86	157.12	831.565	90.96	75.12	-35.33
JEA175CS50x0.95	175	50	0.95	20.0	5.00	295.02	2.310	1,200.058	13.715	63.78	100.965	2.806	18.50	14.02	21.96	88.75	697.389	91.02	75.30	-35.50
JEA150CS45x1.45	150	45	1.45	8.0	5.00	362.46	2.838	1,078.251	14.377	54.54	79.099	2.177	14.39	10.50	16.42	254.03	342.197	83.82	62.20	-26.20
JEA150CS45x1.15	150	45	1.15	8.0	5.00	288.55	2.259	863.139	11.509	54.69	60.834	1.762	14.52	10.47	16.58	127.20	279.176	83.89	62.47	-26.47
JEA150CS45x0.95	150	45	0.95	8.0	5.00	238.97	1.871	717.436	9.566	54.79	50.962	1.475	14.60	10.44	16.68	71.89	234.984	83.94	62.65	-26.65
JEA100CS45x1.15	100	45	1.15	12.5	5.00	241.40	1.890	367.979	7.360	39.04	63.639	2.071	16.24	14.28	19.98	106.42	144.902	56.44	54.06	-33.68
JEA100CS45x0.95	100	45	0.95	12.5	5.00	200.02	1.566	306.172	6.123	39.12	53.257	1.733	16.32	14.26	20.08	60.17	122.141	56.59	54.26	-33.87
JEA100CS45x0.75	100	45	0.75	12.5	5.00	158.38	1.240	243.451	4.869	39.21	42.590	1.385	16.40	14.25	20.17	29.17	98.384	56.74	54.45	-34.05
JEA75CS45x1.15	75	45	1.15	10.5	5.00	208.05	1.629	188.438	5.025	30.10	53.747	1.822	16.07	15.50	20.35	91.72	70.853	49.16	49.08	-35.28
JEA75CS45x0.95	75	45	0.95	10.5	5.00	172.47	1.350	157.027	4.187	30.17	45.000	1.525	16.15	15.49	20.44	51.88	59.885	49.34	49.28	-35.46
JEA75CS45x0.75	75	45	0.75	10.5	5.00	136.63	1.070	125.049	3.335	30.25	36.005	1.220	16.23	15.48	20.53	25.62	48.367	49.51	49.49	-35.54

Notes:

Ix, Iy Moment of Inertia about centroidal principal axis Sx, Sy Section Modulus about centroidal principal axis rx, ry Radius of Gyration about centroidal principal axis m Distance between shear center and web centerline J St. Venant Torsion Constant

Cw Warping Constant

j Parameter used in determination of Elastic moment ro Polar Radius of Gyration about shear center vo Distance between centroida and shear center







533 Commonwealth Avenue Matandang Balara 1119 Quezon City Tel. Nos.: (02) 8847-8335

